



DuraCoat
ASK THE EXPERTS

Duracoat Ultima Aqua Gloss Enamel

Features

- Quick drying
- Non yellowing
- Odourless
- Outstanding stain resistance
- Excellent flow and brushability, similar to solvent based enamel
- Excellent gloss retention
- No added lead

General Description

Duracoat Ultima Aqua Gloss Enamel is a premium quality non-yellowing high gloss finish suitable for use on interior and exterior metal, wood and plastered surfaces, both new and previously painted. It has excellent adhesion, colour retention, good durability and is virtually odour free as compared to conventional solvent based gloss finish.


Recommended for

Ideal for furniture, doors, skirtings and wall surfaces in kitchen and bathrooms.

Limitations

Do not apply when the temperature is below 10°C.

Product Information

Colour Range : Available in a wide range of colors from Duracoat Color Chart, Duracoat Classic Fandek and Duracoat Colour Plus Fandek	Technical Data	
	Finish	Gloss
Special Colors : Special colors can be made available on request	Spread Rate	11-13 Sq. Mt./Ltr when applied on a smooth surface.
	Drying time	
Pack sizes : 1ltr, 4 ltrs, 20 ltrs	- Surface dry	30 mins
	- Recoating time	4 hours
Technical Assistance: If in doubt please contact our Technical department on 82355/954	Application	By Brush, Conventional Spray
	Thinning	DO NOT THIN. Product is ready for use.
 <p>DuraCoat ECO FRIENDLY PAINT ASK THE EXPERTS This product is environmentally friendly and has low VOC (volatile organic compounds)</p>	Cleaning	Clean all equipments with water. Spray equipment should be given a final rinse with white spirit to prevent rusting.
	Volatile Organic Compounds (VOC)	< 50 gms/ltr

Duracoat Ultima Aqua Gloss Enamel

Surface Preparation

All surfaces to be painted must be clean, dry and free from dusts, grease or any loose material. Cracks and defects should be filled with appropriate crack filler followed by appropriate primer.

New Unpainted surfaces:

Cement plaster, Gypsum plaster : Apply one coat of Duracoat Universal Undercoat or Duracoat Alkali Resistant Primer.

Wood : For new wood apply Duracoat Aqua Wood Primer.

Metal: Remove any rust by sanding, mechanical grinding or wire brushing. Apply one coat of Duracoat Rust Guard Metal Primer

Previously painted surface :

Remove loose and flaking paint back to sound substrate by scrapping and sanding. Sand glossy enamel surfaces thoroughly to an even matt finish, dust off. Follow the procedure as for new unpainted surfaces.

Finish : Apply 2-3 coats of Duracoat Ultima Aqua Gloss Enamel.

Precautions

- Ensure good ventilation during application and drying
- Store the product at ambient conditions in well ventilated locations and away from the source of ignition and fire
- Avoid eye and skin contact. In case of eye and skin contact, wash with plenty of clean water. If symptoms persists seek medical advise
- Do not inhale or inject. In case of inhalation move to fresh air and seek medication attention if symptoms persists in both the cases.
- Use appropriate personal protective equipments.
- In high humidity areas, use of a bio wash solution is recommended to remove surface fungus growth, fungal spores, mould, etc before application of the paint system.

Application

- Stir thoroughly before and during use
- Always use good quality brush
- Try to paint in one motion
- Always pre test on a small area first

Note

- When over coating a dark shade with a light shade three coats may be required
- On dark shades like bright Reds, Greens, Oranges an additional coat will be required as some shades have low opacity

Post Application Instructions

The best thing to remove wall stains is to remove it immediately.

For removing stains, sponge clean with mild soap/detergent solution and wipe clean.

For better washability ensure the paint surface is cured for 1 week.

KEEP OUT OF REACH OF CHILDREN

Refer to MSDS for additional health and safety information

Disclaimer

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by Basco Products (K) Ltd. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Basco Products (K) Ltd. representative to obtain the most recent Product Data Information