

Duracoat Royale Sunproof Roof Paint

Product Description:

Duracoat Royale Sunproof Roof Paint is an extremely durable, weather resistance and fully flexible coating for roofs. The tough formulation is resistant to UV light and offers superior water resistance. Advanced pigments and light stabilisers ensure that the wide range of colours remain true.

Features/Benefits:

- Excellent durability
- 100% Acrylic emulsion formulation
- UV resistant pigments, colours remain true for a long time
- Excellent obliteration
- Long lasting protection of roofs
- Excellent adhesion (no peeling), highly durable and weather resistant
- Repels water and will not soften and peel off
- Easy cleaning, no solvent smell, user and environment friendly
- Aesthetic appeal – beautiful, smooth appearance

Application methods:

For detailed information please refer to the instructions on the container.

- Can be applied by brush, roller or airless spray
- Stir well before use

Thinning:

DO NOT thin. Paint is ready to apply.

Spreading rate:

Spreading rate varies according to the surface porosity and texture. Approximate spreading rates on different surfaces are given below.

Fibre-Cement tiles	7 Sq.Mt/Ltr.
Galvanised Sheet	9 Sq.Mt/Ltr.
Granular Cement tiles	2-4 Sq.Mt/Ltr.

Shade range:

Available from Royale colour book.

Pack Sizes:

Available in 1 Ltr, 4 Ltrs, and 20 Ltrs.

Good working practices:

- Read instructions carefully before painting
- Ensure good ventilation during paint application
- When using spray gun as an application tool, wear suitable clothing and protective equipments
- Wash hands with water and soap
- Keep unused paint cans tightly closed and away from children and pets

Hints and tips (for best results)

- Always read instructions
- Always use good quality brush
- Try to paint in one motion
- Always pre test on a small area first

Wise precautions:

- Ensure good ventilation during application and drying
- Avoid contacts with skin and eyes
- After contact with skin wash immediately with plenty of soap and water. In case of contact with eye, rinse immediately with plenty of water and seek medical advice.
- Keep out of reach of children

Duracoat Royale Sunproof Roof Paint

Please read carefully to get optimum performance from this high quality product.

- Stir well till homogeneous
- Take a small quantity of paint, thin to brushable viscosity and apply on a small area on the prepared surface to confirm shade and finish. This will avoid redoing the whole work if the shade is not suitable to your taste

Duracoat Royale Sunproof Roof Paint is an extremely durable, weather resistance and fully flexible coating for roofs. The tough formulation is resistant to UV light and offers superior water resistance. Advanced pigments and light stabilisers ensure that the wide range of colours remain true.

Surface Preparation

Galvanised roof: Clean new surfaces with fresh water thoroughly. Dry and prime with Duracoat etch primer. Rust if any, should be sanded to bright metal and prime with Duracoat etch primer. Do light sanding. Then apply one coat of Duracoat Zinc Phosphate Primer. Allow it to dry for 24 hours. Apply two coats of undiluted Duracoat Royale Sunproof Roof Paint. For previously painted surface loose paint, chalk and dirt should be removed by scrapping, sanding and cleaning with water before applying etch primer.

Granular tiles, asbestos fibre-cement tiles, Clay tiles: For new and previously painted surface in good condition, remove dust, dirt, loose granules, friable and powdery material by scrubbing with hard bristle brush and water. Allow surface to dry. Apply one coat of Duracoat Pliolite Surface Conditioner. Allow it dry for 24 hours. Then apply two coats of undiluted Duracoat Royale Sunproof Roof Paint. Previously painted surface in poor condition should be stripped out completely.

Application: Can be applied by brush, roller or airless spray. **Do Not** thin. Paint is ready to apply.

Spreading capacity: Approx. 7 Sq.Mt/Ltr on Fibre-Cement tiles, 9 Sq.Mt/Ltr on Galvanised tiles, 2-4 Sq.Mt/Ltr on Granular Cement tiles.

Drying: Touch dry in 30 minutes, overcoatable within 3 – 4 hours under normal drying conditions.

Stir well before use, clean equipment with water.

If in doubt please contact our Technical department on 82355/954