

DURACOAT TWO PACK EPOXY FLOOR PAINT

Product Description: Duracoat Two Pack Epoxy Floor is a two component epoxy system highly resistant against abrasion, chemical attack and water penetration. It offers maximum resistance to pedestrian and vehicular traffic. It is recommended for use on concrete floors in chemical plants, laboratories, hospitals, dairies, breweries, food factories, bottling plants, showrooms etc.

Finish: Gloss

Application: By Brush, roller or spray

Thinning: Use Duracoat Epoxy Thinner only.

Drying time: Surface Dry: 3-4 hours
Re-coating: 24 hours – 30hours strictly.

Cleaning: Clean all equipment with Duracoat Two Pack Epoxy Thinner immediately.

Colour Range: White, Black, Grey, Green, Blue, Red and Orange

Spread Rate: 9-12sq. mts. per litre when applied on smooth surface. Spread rate will vary if applied on rough surfaces

Pack Sizes: 1 litre, 4 litres

SPECIFICATIONS:

Mixing: The two components, paint and hardener (base and hardener) must be mixed on site at volume ratios of 3:1 (75% base and 25% hardener). Allow to stand for 20 minutes before use. Ensure that only required material is mixed, as mixed material's pot life is 8 hours. Apply a second coat after 24 hours, but not more than 30 hours. Maximum chemical and physical resistance is achieved after 7 days. Two coats are recommended for optimum protection.

New Unpainted Concrete Surface: Make sure the surface is free from dust, grease, oil and contains no water (moisture). Apply one coat of Duracoat Two Pack Epoxy clear followed by 2-3 coats of desired colour allowing 24 hours drying time between coats. The first coat should be thinned slightly more than the other two coats using Duracoat Two Pack Epoxy Thinner

Previously painted Surfaces with similar product: Clean the surface and remove loose flakes and sand down to rough surface. Apply 2-3 coats of Duracoat Two Pack Epoxy Floor Paint allowing 24 hours drying time between coats.

Please note:

When applying Duracoat Two Pack Epoxy Floor by spray, face mask and goggles should be worn. Avoid contact with skin and eyes. Use in well ventilated areas.

After the seven days full cure, the coating is safe in premises where food processing, pharmaceutical and other such related processing take place.