

Product Name: CRYSTALLINE Crystal Effect Coating Product Code: 110

DESCRIPTION

CRYSTALLINE is a water-based decorative finish for indoor use, consisting of waterborne styreneacrylic emulsion enriched with metallic pigments and special fillers.

SPECIFICATION

- ✓ CRYSTALLINE features a unique crystalline effect that stands out most when near light sources.
- ✓ CRYSTALLINE is washable
- ✓ The product is non-hazardous if used according to its specifications.
- CRYSTALLINE can be applied to all kinds of plaster surfaces, as well as wood and metal panels, as long as they are treated with appropriate primers.

APPLICATION INSTRUCTIONS

Ensure that the surface is clean, dry and free from peeling paint or any substance that may compromise adhesion.

Prime the surface using the specific decorative primer Sandeco Uniprimer.

Using a varnish brush, apply first coat of Crystalline thinned with %25 of water and let them dry for minimum 3 hours before applying the finish.

Spread the product onto the surface with alternate brushstrokes, taking care to level the amount evenly.

Make sure that both the ambient temperature and the substrate temperature are between +5°C and +35°C

Deka BOYA İTHALAT İHRACAT SAN.TİC.LTD.ŞTİ. Merkez :Atatürk Mahellesi Ekincioğlu sokak No:21 / 1 Ataşehir–İstanbul/TÜRKİYE Tel:+90(216) 688 33 52(Pbx) Fax: +90(216) **Fabrika:**S.S.İstanbul Mermerciler Küçük San.Sitesi Yapı Koop. 34.Cd.No:3 41490 Gebze-Kocaeli/TÜRKİYE Tel:+90(262) 728 10 88 (Pbx) Fax: +90(262) 728 10 71 www.dekaboya.com.tr e-mail: dekaboya@dekaboya.com.tr



Product Name: CRYSTALLINE

Crystal Effect Coating Product Code: 110

TECHNICAL FEATURES & PHYSICAL CONSTANTS

COLOURS

DENSITY VISCOSITY PH VOLUME SOLIDS, % GLOSS GRADE FLASH POINT THINNING DRYING TIME

COVERAGE

TEMPERATURE FOR APPLICATION APPLICATION TOOLS SIZES & PACKAGING STORAGE AND SHELF LIFE WARNING Available in a range of SANDECO special color card which can be further increased with special colors 1,25 ± 0,02 gr/cm³ 115- 125 KU 8 - 9 52 ± 2 Matt Non-flammable. Water Dry-to-touch, 2 - 3 hours / In depth, 24 Hours (recorded at 23°C) Depending on porosity of surface and environmental conditions 0.130 - 0.140 L/m² per coat + 5 °C - + 35 °C Varnish Brush 1Lt - 2,5Lt 1 year, unopened in cool frost-free conditions Keep out of the reach of children. Avoid contact with skin and eves

Deka BOYA İTHALAT İHRACAT SAN.TİC.LTD.ŞTİ. **Merkez** :Atatürk Mahellesi Ekincioğlu sokak No:21 / 1 Ataşehir–İstanbul/TÜRKİYE Tel:+90(216) 688 33 52(Pbx) Fax: +90(216) **Fabrika:**S.S.İstanbul Mermerciler Küçük San.Sitesi Yapı Koop. 34.Cd.No:3 41490 Gebze-Kocaeli/TÜRKİYE Tel:+90(262) 728 10 88 (Pbx) Fax: +90(262) 728 10 71 www.dekaboya.com.tr e-mail: dekaboya@dekaboya.com.tr