

Product Description: Basco Autoguard Cellulose Finish is manufactured from a combination of Nitrocellulose and good quality alkyd resins. It is formulated to give fast drying material with high gloss, excellent build and a very elastic paint film to motorcars, trucks, aircrafts etc. It is formulated to give maximum durability over long periods of time in terms of gloss and colour retention under severe tropical weather conditions.

Finish: High Gloss

Application: By spraying only, recommended spraying pressure @ 45-55 p.s.i.

Thinning: Basco Autoguard Cellulose Finish should be thinned with Basco High Gloss Thinner or Basco Super High Gloss Thinner only, thinned to spraying viscosity of 24-28 seconds B4 cup at 25^o C. Usually a thinning ratio of 1 part paint, 1 part thinner yields this viscosity.

Drying Time: Dust free 5 – 10minutes in fair weather. Recoating recommended 30minute or after.

Cleaning: Clean all equipment with Basco Standard Thinner

Colour: As requested

Priming: Basco Autoguard Cellulose Finish is best used on Cellulose Grey Primer Surfaces.

Polishing: Polishing using Rubbing compound may be done to achieve a higher glaze on the surface after 7 days.

Pack Sizes: ½ litre, 1 litre, 4 litres.

SPECIFICATIONS

Surface Preparation: All surfaces to be painted must be dry, clean and free from rust, dirt, oil, grease or any other contaminants, but primed appropriately. In case of previously painted surfaces ensure that all loose or flaking materials are completely removed prior to painting. For good adhesion between coats, it is recommended that surfaces be rubbed down with wet or dry abrasive paper.

Caution

- Spray in well ventilated areas only
- Wear eye goggles and protective clothing when spraying
- Do not use or keep near naked flames. **HIGHLY INFLAMMABLE**
- Avoid contact with skin or eyes.