

## Duracoat Floprime Sealer

### General Description

Duracoat Floprime Sealer is a Two Component solvent free Epoxy primer for cementitious substrate.

### Recommended for

For priming of concrete and screeds prior to overcoating with Duracoat Floseal SL or Duracoat Floseal SF500.

### Limitations

Do not apply when the temperature is below 10°C.

### Product Information

<b>Colour:</b> Clear	<b>Technical Data</b>	
	<b>Finish</b>	Gloss
	<b>Spread Rate</b>	5-7 m <sup>2</sup> /ltr. Coverage can vary greatly depending on the surface porosity.
<b>Pack sizes :</b> 1 ltr (0.75 ltr Base+ 0.25 ltr Hardener) 4 ltr (3 ltr Base + 1ltr Hardener)	<b>Thinning</b> Base: Hardener= 3:1 by volume	
<b>Technical Assistance:</b> If in doubt please contact our Technical department on 6823555/954	<b>Pot Life</b>	30 mins @ 25°C
	<b>Curing Time</b>	Can be overcoated after 12 hours Maximum overcoat time – 24 hours Full cure – 7 days
	<b>Cleaning</b> Clean all equipments with water. Spray equipment should be given a final rinse with Duracoat White Spirit to prevent rusting	

### Surface Preparation

Concrete surface to be laid must be flat and roughened and cured for 28 days. Remove laitance preferably by using Blast tracking machine or diamond grinding machine with vacuum sucking off the dust.

### Application Procedure

Add component B into component A and stir the mixture for a period of 3 minutes using a low speed electric mixer until the mixture becomes homogenous. Avoid stirring more than necessary in order to minimize entrapped air inside the mixture. Ready mixed product should be used within 30 mins.

### Precautions

- Ensure good ventilation during application and drying
- Store the product at ambient conditions in well ventilated locations and away from the source of ignition and fire
- Avoid eye and skin contact. In case of eye and skin contact, wash with plenty of clean water. If symptoms persists seek medical advise
- Do not inhale or inject. In case of inhalation move to fresh air and seek medication attention if symptoms persists in both the cases.
- Use appropriate personal protective equipments.
- In high humidity areas, use of a bio wash solution is recommended to remove surface fungus growth, fungal spores, mould, etc before application of the paint system.

**KEEP OUT OF REACH OF CHILDREN  
PROTECT FROM FREEZING**

**Refer to MSDS for additional health and safety information**

#### **Disposal information:**

Dispose of in accordance with County regulations. Dry, empty containers may be given to scrap dealers for recycling.

### Disclaimer

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by Basco Products (K) Ltd. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Basco Products (K) Ltd. representative to obtain the most recent Product Data Information

Basco Products (K) Ltd. P.O. Box 34424-00100, North Airport Road, Embakasi, Nairobi, Kenya  
Tel:+254-20-6823555/954, Fax: +254-20-6823956 [www.bascopaints.com](http://www.bascopaints.com)